



Den Braven

Clearsil

Crystal clear acetoxysilicone sealant



PRODUCT DESCRIPTION

Zwaluw Clearsil is a crystal clear acetoxysilicone sealant which cures by reacting to moisture to form a durable elastic rubber seal.

KEY BENEFITS

- Crystal clear
- Adhesive and sealant
- Good mechanical properties

APPLICATIONS

Zwaluw Clearsil was specifically developed for crystal clear bonding and sealing of full glass construction (1) out of single glass such as showcases, furniture and other glass decorations.

Remark (1)
Compatibility of the edge seals of insulation glass with glazing sealants cannot be guaranteed by the supplier of the sealant, as the composition of the edge seals can be changed by the producer without notice. Advice on the compatibility of glazing sealants to the edge seals of insulation glass is based on experience and therefore not guaranteed.

DIRECTION FOR USE

When using Zwaluw Clearsil a shrinkage of 30% should be allowed for. As a result, tension will occur on the substrate. Ask for advice in advance. For further questions please contact our technical service.

TECHNICAL SPECIFICATIONS

100% Modulus	DIN 53504 S2	0,30 N/mm ²
Application Temperature		+5°C to +40°C
Base		Acetoxysilicone
Application Rate	@ Ø3 mm/6,3 bar	200 g/min
Curing Time	@ +23°C/50% RH	2 mm/24 hours
Density	ISO 1183-1	0.95 g/ml
Elongation At Break	DIN 53504 S2	800%
Flow	ISO 7390	<2mm
Frost Resistance		Up to -15°C
Shore A Hardness	DIN 53505	12
Skin Formation	+23°C/50% RH (DBTM 16)	5-6 minutes
Temperature Resistance		-40°C to +180°C
Tensile Strength	DIN 53504 S2	1.50 N/mm ²

These are typical values

LIMITATIONS

- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates, Not suitable for applications on concrete, marble, lead, copper and galvanized steel, Not suitable for aquariums and terrariums

SURFACE PREPARATIONS AND FINISHING

Application temperature: +5°C to +40°C (applies to environment and substrates). All substrates must be solid, clean, dry, and free from grease and dust. Clean substrates with Zwaluw Cleaner. Zwaluw Clearsil adheres perfectly without the use of a primer to most non porous substrates, like glass, painted wood, ceramic and enamelled. Always test adhesion prior to application. Use Zwaluw Finisher to smoothen the joint.

PAINTABILITY

Zwaluw Clearsil is not paintable. We recommend covering the edges of the joint with masking tape to prevent surfaces that need to be painted from being contaminated silicone.

CLEANING

Uncured material and tools can be cleaned by using Zwaluw Cleaner. Cured material can only be mechanically removed. Hands can be cleaned with Zwaluw Wipes.

PACKAGING DESCRIPTION

Cartridge

COLOUR

Transparent

SHELF LIFE

In unopened original packaging between +5°C and +25°C, shelf life up to 12 months from production date, stored in a dry place.

CERTIFICATIONS

- EN 15651-2: G-CC
- EN 15651-1: F-EXT-INT-CC
- A+ French VOC Regulation



HEALTH & SAFETY

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

WARRANTY & GUARANTEE

Bostik warrants that its product complies, within its shelf life, to its specification.

DISCLAIMER

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.



HOTLINE

Smart help +31 162 491 000